

TECHNICAL DATA SHEET

CN303

Polybutadiene Dimethacrylate

DESCRIPTION

CN303, polybutadiene dimethacrylate, is a flexible, hydrophobic oligomer with excellent electrical properties. Cured films of CN303 resist acid, alkali, and high humidity.



SHELF LIFE

Store in the original, closed container in a dry, cool (<45°C) and well-ventilated place. Keep away from frost and heat (open flames, hot surfaces and sources of ignition) sources. Typical shelf-life is 6 months from delivery date for unopened containers. In cases where product sampling is required to carry out incoming quality tests, shelf-life should be maintained beyond opening, provided that it is tightly closed immediately after and that contamination with foreign bodies is avoided. Inhibitors have been added to enhance storage stability. They require the presence of air in the container in order to improve their efficiency. Keep stabilizer levels constant to avoid explosive polymerization. An air space is required above the liquid in all containers

STORAGE

See SDS for Storage Considerations

HEALTH AND SAFETY

See SDS for Health & Safety Considerations

LIQUID PROPERTIES

Appearance	Clear liquid
Density at 25°C (g/mL)	0.9698
Refractive Index at 25°C	1.515
Functionality	2
Color (Gd)	10

CURED PROPERTIES

Tg (°C), by DSC	-35
Young Modulus (MPa)	3
Elongation at break (%)	49
Tensile Strength (MPa)	1

PRODUCT PERFORMANCE

Wood Adhesion
Chemical Resistance
Moisture Resistance
Flexibility
ABS/PC Adhesion
PVC/PS Adhesion
Corrosion Resistance

SPECIAL FEATURE

Hydrophobic

SUGGESTED APPLICATIONS

Adhesives & sealants
Electronics

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80
www.Sartomer.arkema.com