

TECHNICAL DATA SHEET

CN9002

Aliphatic Urethane Acrylate Oligomer

DESCRIPTION

CN9002 is a difunctional aliphatic urethane acrylate oligomer characterized by low color and low viscosity. It is non-yellowing and imparts softness and flexibility to adhesives, coatings, and inks.



SHELF LIFE

Store in the original, closed container in a dry, cool (<45°C) and well-ventilated place. Keep away from frost and heat (open flames, hot surfaces and sources of ignition) sources. Typical shelf-life is 6 months from delivery date for unopened containers. In cases where product sampling is required to carry out incoming quality tests, shelf-life should be maintained beyond opening, provided that it is tightly closed immediately after and that contamination with foreign bodies is avoided. Inhibitors have been added to enhance storage stability. They require the presence of air in the container in order to improve their efficiency. Keep stabilizer levels constant to avoid explosive polymerization. An air space is required above the liquid in all containers

STORAGE

See SDS for Storage Considerations

HEALTH AND SAFETY

See SDS for Health & Safety Considerations

LIQUID PROPERTIES

Functionality	2
Appearance	Clear liquid
Refractive Index at 25°C	1.46
Density at 25°C (g/mL)	1.1032
Color (Pt/Co or APHA)	<100

CURED PROPERTIES

Tg (°C), by DSC	-50
Young Modulus (MPa)	2
Elongation at break (%)	116
Tensile Strength (MPa)	1

PRODUCT PERFORMANCE

Flexibility
Weatherability
ABS/PC Adhesion
Metal Adhesion
PVC/PS Adhesion
Wood Adhesion
Chemical Resistance
Corrosion Resistance
PE/PET/PP/PMMA Adhesion
Moisture Resistance

SUGGESTED APPLICATIONS

Adhesives & sealants
Industrial flooring & waterproofing
Inkjet inks

Arkema Inc
502 Thomas Jones Way
Exton, PA 19341 – AMERICA
www.Sartomer.arkema.com

Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex
France
www.Sartomer.arkema.com