

TECHNICAL DATA SHEET

CN9039

Aliphatic Urethane Acrylate Oligomer

DESCRIPTION

CN9039 is an oligomer that offers low viscosity, good abrasion and heat resistance.



SHELF LIFE

Store in the original, closed container in a dry, cool (<45°C) and well-ventilated place. Keep away from frost and heat (open flames, hot surfaces and sources of ignition) sources. Typical shelf-life is 6 months from delivery date for unopened containers. In cases where product sampling is required to carry out incoming quality tests, shelf-life should be maintained beyond opening, provided that it is tightly closed immediately after and that contamination with foreign bodies is avoided. Inhibitors have been added to enhance storage stability. They require the presence of air in the container in order to improve their efficiency. Keep stabilizer levels constant to avoid explosive polymerization. An air space is required above the liquid in all containers

STORAGE

See SDS for Storage Considerations

HEALTH AND SAFETY

See SDS for Health & Safety Considerations

LIQUID PROPERTIES

Appearance	Clear liquid
Functionality	6
Color (Pt/Co or APHA)	<100
Density at 25°C (g/mL)	1.1835
Refractive Index at 25°C	1.49

CURED PROPERTIES

Tg (°C), by DSC	145
Elongation at break (%)	1
Tensile Strength (MPa)	76
Young Modulus (MPa)	3344

PRODUCT PERFORMANCE

Hardness
Stain Resistance
Weatherability
Abrasion Resistance
Chemical Resistance
Scratch Resistance
Moisture Resistance
Corrosion Resistance

SPECIAL FEATURE

High functionality

SUGGESTED APPLICATIONS

Adhesives & sealants
Inkjet inks
Wood coatings

Arkema Inc
502 Thomas Jones Way
Exton, PA 19341 – AMERICA
www.Sartomer.arkema.com

Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex
France
www.Sartomer.arkema.com