

TECHNICAL DATA SHEET

CN965

Aliphatic Urethane Acrylate

DESCRIPTION

CN965 is an aliphatic polyester based urethane diacrylate oligomer. It is a flexible oligomer offering good weatherability. This product can be made with no intentionally added tin.



No Intentionally Added Tin



SHELF LIFE

Store in the original, closed container in a dry, cool (<45°C) and well-ventilated place. Keep away from frost and heat (open flames, hot surfaces and sources of ignition) sources. Typical shelf-life is 6 months from delivery date for unopened containers. In cases where product sampling is required to carry out incoming quality tests, shelf-life should be maintained beyond opening, provided that it is tightly closed immediately after and that contamination with foreign bodies is avoided. Inhibitors have been added to enhance storage stability. They require the presence of air in the container in order to improve their efficiency. Keep stabilizer levels constant to avoid explosive polymerization. An air space is required above the liquid in all containers

STORAGE

See SDS for Storage Considerations

HEALTH AND SAFETY

See SDS for Health & Safety Considerations

LIQUID PROPERTIES

Appearance	Clear liquid
Density at 25°C (g/mL)	1.1012
Refractive Index at 25°C	1.48
Surface Tension at 20°C (mN/m)	34.9
Functionality	2
Color (Pt/Co or APHA)	<100

CURED PROPERTIES

Tg (°C), by DSC	-37
Young Modulus (MPa)	21
Elongation at break (%)	57
Tensile Strength (MPa)	5

PRODUCT PERFORMANCE

Shrinkage
Flexibility
Wood Adhesion
ABS/PC Adhesion
Metal Adhesion
PVC/PS Adhesion
Weatherability
PE/PET/PP/PMMA Adhesion
Moisture Resistance
Corrosion Resistance

SUGGESTED APPLICATIONS

Adhesives & sealants
Composites
Flexographic inks
Inkjet inks
Metal coatings
Screen inks

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80
www.Sartomer.arkema.com