


TECHNICAL DATA SHEET

SR335

Lauryl Acrylate

DESCRIPTION

SR335 is a low volatility monofunctional monomer with a long chain aliphatic hydrophobic backbone.



LIQUID PROPERTIES

Appearance	Clear liquid
Functionality	1
Color (Pt/Co or APHA)	<70
Viscosity at 25°C (mPa.s or cPs)	6
Density at 25°C (g/mL)	0.8776
Molecular Weight (g/mol)	240
Refractive Index at 25°C	1.4416
Surface Tension at 20°C (mN/m)	30.3

CURED PROPERTIES

Tg (°C), by DSC	-30
-----------------	-----

PRODUCT PERFORMANCE

Flexibility
Moisture Resistance
Corrosion Resistance
Shrinkage
Scratch Resistance
Abrasion Resistance
Weatherability
Chemical Resistance

SPECIAL FEATURE

Hydrophobic

SUGGESTED APPLICATIONS

Adhesives & sealants
Conformal coatings
Electrical potting & encapsulation
Electronics
Flexographic inks
Inkjet inks
Optical fibers
Overprint varnishes
Polymer synthesis
Wood coatings

SHELF LIFE

Store in the original, closed container in a dry, cool (<45°C) and well-ventilated place. Keep away from frost and heat (open flames, hot surfaces and sources of ignition) sources. Typical shelf-life is 6 months from delivery date for unopened containers. In cases where product sampling is required to carry out incoming quality tests, shelf-life should be maintained beyond opening, provided that it is tightly closed immediately after and that contamination with foreign bodies is avoided. Inhibitors have been added to enhance storage stability. They require the presence of air in the container in order to improve their efficiency. Keep stabilizer levels constant to avoid explosive polymerization. An air space is required above the liquid in all containers

STORAGE

See SDS for Storage Considerations

HEALTH AND SAFETY

See SDS for Health & Safety Considerations

Arkema Inc
502 Thomas Jones Way
Exton, PA 19341 – AMERICA
www.Sartomer.arkema.com

Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex
France
www.Sartomer.arkema.com