


TECHNICAL DATA SHEET

SR423

Isobornyl Methacrylate

DESCRIPTION

SR423 is an excellent reactive diluent for oligomers. The cyclic group produces polymers through free radical curing which have a high glass transition temperature.



LIQUID PROPERTIES

Appearance	Clear liquid
Functionality	1
Color (Pt/Co or APHA)	<75
Viscosity at 25°C (mPa.s or cPs)	11
Density at 25°C (g/mL)	0.9819
Refractive Index at 25°C	1.474
Surface Tension at 20°C (mN/m)	31
Molecular Weight (g/mol)	222

CURED PROPERTIES

Tg (°C), by DSC	110
-----------------	-----

PRODUCT PERFORMANCE

Hardness
Chemical Resistance
Shrinkage
Wood Adhesion
Stain Resistance
Moisture Resistance
Weatherability
Corrosion Resistance

SPECIAL FEATURE

Hydrophobic

SUGGESTED APPLICATIONS

Adhesives & sealants
Artificial marble
Composites
Conformal Coatings
Electrical potting & encapsulation
Electronics
Industrial flooring & waterproofing
Metal coatings
Nail varnishes
Polymer synthesis

SHELF LIFE

Store in the original, closed container in a dry, cool (<45°C) and well-ventilated place. Keep away from frost and heat (open flames, hot surfaces and sources of ignition) sources. Typical shelf-life is 6 months from delivery date for unopened containers. In cases where product sampling is required to carry out incoming quality tests, shelf-life should be maintained beyond opening, provided that it is tightly closed immediately after and that contamination with foreign bodies is avoided. Inhibitors have been added to enhance storage stability. They require the presence of air in the container in order to improve their efficiency. Keep stabilizer levels constant to avoid explosive polymerization. An air space is required above the liquid in all containers

STORAGE

See SDS for Storage Considerations

HEALTH AND SAFETY

See SDS for Health & Safety Considerations

Arkema Inc
502 Thomas Jones Way
Exton, PA 19341 – AMERICA
www.Sartomer.arkema.com

Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex
France
www.Sartomer.arkema.com