


TECHNICAL DATA SHEET

SpeedCure 939


4-isopropyl-4'-methyldiphenyliodonium tetrakis (pentafluorophenyl)borate

DESCRIPTION

SpeedCure 939 is cationic photoinitiator of the iodonium borate family with absorption maximum at 258 nm. SpeedCure 939 provides high reactivity and solubility in cationic systems when used at 0.5-5 wt% in UV curable formulations and LED curable formulations when sensitised with thiox-anthones.



UV SPECTRUM



SHELF LIFE

Typical shelf-life is **24** months from the manufacture date for un-opened containers. In cases where product sampling is required to carry out incoming quality tests, shelf-life should be maintained beyond opening, provided that it is tightly closed immediately after and that contamination with foreign bodies is avoided.

STORAGE AND HANDLING

Store in the dark in the original, closed container, in a dry, cool (20-°C) and well-ventilated place.
Keep away from frost and heat (open flames, hot surfaces and sources of ignition) sources.

HEALTH AND SAFETY

See SDS for Health & Safety Considerations

SALES SPECIFICATIONS

Appearance	White to off-white solid
Purity (%)	≥ 99.0
Water Content (%)	≤ 0.5

PERFORMANCE

Depth Cure
LED
Pigmented Systems
Surface Cure

SUGGESTED APPLICATIONS

3D printing
Composites
Industrial coatings

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80
www.Sartomer.arkema.com