


TECHNICAL DATA SHEET

SpeedCure MBP

4-methylbenzophenone

DESCRIPTION

SpeedCure MBP is a Norrish Type II photoinitiator from the benzophenone family, with absorption maximum at 259 nm. SpeedCure MBP provides high reactivity and surface cure when used at 0.5-5 wt% and combined with an amine synergist in UV curable formulations.



SHELF LIFE

Typical shelf-life is **24** months from the manufacture date for un-opened containers. In cases where product sampling is required to carry out incoming quality tests, shelf-life should be maintained beyond opening, provided that it is tightly closed immediately after and that contamination with foreign bodies is avoided.


STORAGE AND HANDLING

Store in the dark in the original, closed container, in a dry, cool (20-°C) and well-ventilated place.
Keep away from frost and heat (open flames, hot surfaces and sources of ignition) sources.

HEALTH AND SAFETY

See SDS for Health & Safety Considerations

UV SPECTRUM



SALES SPECIFICATIONS

Appearance	White flakes
Purity (%)	≥ 98.0
Melting Range (°C)	55.0 - 58.0
Loss on Drying (%)	≤ 0.25

PERFORMANCE

Clear Coatings
Low Yellowing
Pigmented Systems

SUGGESTED APPLICATIONS

Flexographic inks
Industrial coatings
Offset inks
Overprint varnishes
Screen inks
Wood coatings

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80
www.Sartomer.arkema.com