


TECHNICAL DATA SHEET

SpeedCure XFs


A formulation of 2-hydroxy-2-methyl-1-phenylpropan-1-one and 2,3-dihydro-6-(2-hydroxy-2-methyl-1-oxopropyl)-1,1,3-trimethyl-3-[4-(2-hydroxy-2-methyl-1-oxopropyl)phenyl]-1H-indene

DESCRIPTION

SpeedCure XFs is a formulation of difunctional and monofunctional Norrish Type I photoinitiators from the hydroxyacetophenone family, with an absorption maximum at 252 nm. SpeedCure XFs provides low yellowing, surface cure and increased reactivity when used at 0.5-5 wt% in UV curable formulations.



UV SPECTRUM



SHELF LIFE

Typical shelf-life is **24** months from the manufacture date for unopened containers. In cases where product sampling is required to carry out incoming quality tests, shelf-life should be maintained beyond opening, provided that it is tightly closed immediately after and that contamination with foreign bodies is avoided.

STORAGE AND HANDLING

Store in the dark in the original, closed container, in a dry, cool (20-°C) and well-ventilated place.
Keep away from frost and heat (open flames, hot surfaces and sources of ignition) sources.

HEALTH AND SAFETY

See SDS for Health & Safety Considerations

SALES SPECIFICATIONS

Appearance	Pale yellow clear liquid
Water Content (%)	≤ 0.5
Color (20%w/v Acetone, Gd)	≤ 7.0
Extinction Coefficient (M-1 cm-1)	≥ 450.0

PERFORMANCE

Clear Coatings
Low Odor
Low Yellowing
Surface Cure

SUGGESTED APPLICATIONS

Adhesives & sealants
Flexographic inks
Industrial coatings
Inkjet inks
Offset inks
Overprint varnishes
Screen inks
Wood coatings

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80
www.Sartomer.arkema.com