

TECHNICAL DATA SHEET

CN294 E

Acrylated Polyester Oligomer

DESCRIPTION

CN294E is a tetrafunctional oligomer used in UV curable coatings and inks including flexographic, screen, and lithographic inks.



SHELF LIFE

Store in the original, closed container in a dry, cool (<45°C) and well-ventilated place. Keep away from frost and heat (open flames, hot surfaces and sources of ignition) sources. Typical shelf-life is 6 months from delivery date for unopened containers. In cases where product sampling is required to carry out incoming quality tests, shelf-life should be maintained beyond opening, provided that it is tightly closed immediately after and that contamination with foreign bodies is avoided. Inhibitors have been added to enhance storage stability. They require the presence of air in the container in order to improve their efficiency. Keep stabilizer levels constant to avoid explosive polymerization. An air space is required above the liquid in all containers

STORAGE

See SDS for Storage Considerations

HEALTH AND SAFETY

See SDS for Health & Safety Considerations

LIQUID PROPERTIES

Appearance	Clear liquid
Functionality	4
Density at 25°C (g/mL)	1.1173
Refractive Index at 25°C	1.4995
Color (Gd)	<18

CURED PROPERTIES

Young Modulus (MPa)	608
Elongation at break (%)	6
Tensile Strength (MPa)	25

PRODUCT PERFORMANCE

Shrinkage
Wood Adhesion
Weatherability
Hardness
Flexibility
Stain Resistance
Chemical Resistance
Corrosion Resistance
Scratch Resistance
Abrasion Resistance
Moisture Resistance
Pigment Wetting

SPECIAL FEATURE

High functionality

SUGGESTED APPLICATIONS

Electronics
Flexographic inks
Inkjet inks
Metal coatings
Offset inks
Overprint varnishes
Screen inks

Arkema Inc
502 Thomas Jones Way
Exton, PA 19341 – AMERICA
www.Sartomer.arkema.com

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80
www.Sartomer.arkema.com